



MARMO ANTICO

marble-look finish, in lime stucco, for exteriors and interiors

Description	Thick paste composed of: slaked lime, aggregates, mineral pigments, additives of vegetal origin organic compounds specific weight pH thinner	< 5% 1.56-1,60 12 water
Characteristics	Emissions (of the unwaxed finish). steam diffusion μ (of the unwaxed finish)	environmental classification A+ < 10
Notes on lime	Lime materials do not emit environmental pollutants, are permeable to vapor and do not alter the hygrometric balance of old walls. They are not flammable and do not fear microorganisms or mold. Lime materials absorb water in case of rain, but are not damaged by it, and dry quickly. However, if, on exteriors exposed to bad weather or strong environmental pollution, or in interiors subject to intense traffic, you want to prevent the surface from getting wet, it is possible to treat the surface with impregnating agents. Protexan, a water-repellent impregnating agent, and Calceprotect, a water and oil-repellent impregnating agent, are available. They do not significantly alter the vapor permeability of the coverings and keep their appearance unchanged	
Safety	Contains calcium hydroxide, posing the risk of serious eye damage. When handling and using, follow the instructions on the packaging.	
Storage	1 year in the original packaging if stored between +5°C and +40°C	
Supports	As a rule, Marmo Antico is applied on a perfectly smoothed Marmorino Fine Grain coat. On the application of Marmorino Fine Grain, see the Marmorino Tradition sheet. It is also possible to apply Marmo Antico over a coat of Fixaquarz primer. For this it is necessary that the underlying support is perfectly flat and smooth.. Consider anyway that, in this case, more passes will be necessary.	
Laying Rules	Apply between +5°C and +35°C, away from bad weather or excessive sun. Keep in mind that these conditions must remain for the hardening period of the material. Do not use products from different batches on the same wall. Avoid apply fresh material on completely dry material. Apply a new coat when the previous one is almost dry and, if it is too dry and hardened, moisten it slightly before application.	
Laying	Lightly moisten the Marmorino Fine Grain coat. Spread Marmo Antico, as is, with a stainless steel spatula, in a thin layers. Apply at least two coats leveling well. When the last coat begins to harden, smooth it perfectly with the stainless steel spatula kept damp and clean. If the material is too dry, moisten it slightly before smoothing it. To lay on Fixaquarz it is not necessary to humidify it beforehand; proceed to apply the various coats as indicated above, taking into account that at least three coats will be necessary	
Drying	The hardening of the limes begins only after the excess water has evaporated, and can therefore be slower in cold and humid weather. In this case, superficial bleaching may occur, which can be eliminated with acid washes and which in any case tends to disappear over time, but which can be unpleasant. To prevent such bleaching it is possible to treat the dry surface (usually after 48 hours) with Protexan. Note that, however, the hardening of the material is slow and not homogeneous, so the surface, at the beginning, may appear more marbled than it will be when fully hardened.	
Consumption	0,20-0,30 kg/m ² /coat	

This edition cancels and replaces any previous edition. It is the task of Messrs. Customers ensure that this document has not been canceled by a subsequent edition. Edition 2023