



FINTOMARMO

decorative stucco, shiny and washable

Description	Stucco composed of synthetic binders in aqueous emulsion, very fine aggregates, pigments, additives, bactericides	
	specific weight	1.63-1.67
	pH	8-9
	thinner	water
Characteristics	water absorption	very low
	washability	washable
	environmental classification	A
	It is used to obtain glossy stucco coverings of the so-called 'Venetian' type	
Safety	no requirement for specific labelling	
Storage	1 year in the original packaging if stored between +5°C and +40°C	
Supports	It can be applied externally and internally on flat, clean, healthy and dry surfaces These supports must be perfectly smooth and must be previously treated with a coat of good quality washable paint. Before applying the underpainting, perfectly smooth any surfaces that are not flat and smooth Do not apply on surfaces subject to rising damp	
Laying Rules	Laying and drying must be carried out between +5°C and +35°C, protected from bad weather or excessive sun. Do not apply materials from different batches on the same wall	
Laying	<u>Low contrast finish, recommended for large surfaces</u> Spread Fintomarmo in a slightly irregular manner with a stainless steel spatula for stucco (a trapezoidal spatula with rounded edges is recommended). Halfway through drying, smooth the material with the dampened spatula, in order to flatten and make the slightly raised parts shinier. After 4-6 hours, apply a second coat, smoothing it immediately. When this coat is almost dry, smooth it with the spatula held slightly inclined, so as to shine it. <u>Contrasted finish, recommended for small surfaces</u> Spread Fintomarmo in a more irregular manner, using a small stainless steel bodywork spatula. Halfway through drying, smooth the material with the dampened trapezoidal spatula, in order to flatten and make the slightly raised parts shinier. After 4-6 hours, apply a second coat in the same way, smoothing it immediately. When this coat is almost dry, smooth it with the spatula held slightly inclined, so as to shine it Note: Do not polish the completely dry material with the stainless steel spatula, as this could leave blackish traces on the material. To polish hardened material use very fine sandpaper	
Consumption		0,20-0,25 kg/m ² /coat

This edition cancels and replaces any previous edition. It is the task of Messrs. Customers ensure that this document has not been canceled by a subsequent edition. Edition 2023